



TYPICAL PROPERTIES	TEST RESULTS	ASTM
SPECIFIC GRAVITY	1.21	(D792)
DUROMETER HARDNESS, 10 SEC. DELAY	83A	(D2240)
TENSILE STRENGTH	2800 PSI	(D412)
ULTIMATE ELONGATION	330%	(D412)
GRAVES TEAR STRENGTH	280 PPI	(D1004)
100% MODULUS	1450 PSI	(D412)
UV RESISTANCE	YES	
LOW TEMPERATURE BRITTLENESS	-31° F / -35° C	(D746)
OPERATING TEMPERATURE	0° F TO 150° F	
FLAMMABILITY	PASS	U.L. 94 V-0
FLAMMABILITY	PASS	N.F.P.A. 701

IMPORTANT: COMPLETE TEST RESULTS FOR OUTGASSING, ANTI-STATIC AND FLAME SPREAD AVAILABLE UPON REQUEST. WE BELIEVE THESE TESTS TO BE RELIABLE AND ACCURATE TO THE BEST OF OUR KNOWLEDGE BUT CANNOT WARRANTY FOR PROCESSES AND APPLICATIONS BEYOND OUR CONTROL.